

Crystal Structures: NaCl, CsCl, etc.

Dr. Mehnaz Sharmin
Department of Physics
Bangladesh University of Engineering and Technology
Dhaka-1000, Bangladesh


NaCl Structure

- NaCl is a cubic type of ionic crystal.
- FCC type of lattice.

Cl⁻: $8 \times 1/8$ corner + $6 \times \frac{1}{2}$ faces = 4

Na⁺: 12 x ½ edges + 1 center = 4

- So, total 4 NaCl molecules, each NaCl is a basis.
- Each Na⁺ 6 nearest neighbor Cl⁻ and vice versa.
- Nearest neighbor distance = a/2.
- 2nd neighbor distance =a/√2
- Each Na⁺ 12 2nd nearest neighbor
 Na⁺ and vice versa.



Cl⁻: 0 0 0, $\frac{1}{2}$ $\frac{1}{2}$ 0, $\frac{1}{2}$ 0 $\frac{1}{2}$, 0 $\frac{1}{2}$ $\frac{1}{2}$.

Na⁺: $\frac{1}{2}\frac{1}{2}\frac{1}{2}$, $\frac{1}{2}$ 0 0, 0 $\frac{1}{2}$ 0, 0 0 $\frac{1}{2}$.


Packing Factor of NaCl structure

Closest packing along nearest neighbor distance, a/2= $r_{Na}^+ + r_{Cl}^-$

PF =
$$\frac{4 \times \frac{4}{3} \pi [(r_{Na}^{+})^{3} + (r_{Cl}^{-})^{3}]}{[2 (r_{Na}^{+} + r_{Cl}^{-})^{3}]}$$

$$= 0.67$$

Example: LiH, NaCl, KBr, KCl, PbS, NH₄I, AgBr, MgO, MnO, BaO, etc.




CsCl Structure

CsCl is a simple cubic type of ionic crystal.

 Cs^{+} : 8 x 1/8 corner = 1

Cl⁻: 1 body center = 1

- So, total 1 CsCl molecule (basis).
- Each Cs⁺ 8 nearest neighbor Cl⁻ and vice versa.
- Nearest neighbor distance = √3a/2.
- 2nd neighbor distance = a
- Each Cs⁺ 6 2nd nearest neighbor Cs⁺ and vice versa.
- Cs⁺: 0 0 0; Cl⁻: $\frac{1}{2} \frac{1}{2} \frac{1}{2}$.



Packing Factor of CsCl structure

Closest packing along nearest neighbor distance, $\sqrt{3}a/2 = r_{Cs}^+ + r_{Cl}^-$

PF =
$$\frac{1 \times \frac{4}{3} \pi [(r_{Cs}^{+})^{3} + (r_{Cl}^{-})^{3}]}{[2/\sqrt{3} (r_{Cs}^{+} + r_{Cl}^{-}]^{3}}$$

= 0.684

Example: CsCl, CsBr, NH₄Cl, CuZn, TlI,

TlBr, etc.

